

Vergleich Materialproben KITA Ebendorf 2015 April

			ökocontrol	Fraunhofer	Landesamt für Verbraucherschutz						
	Bezeichnung		1-15-04-001/473	AC10111/2015	Probe_015 01.04.	Probe_17 09.04.	Probe_018 09.04.	Probe_019 09.04.	Probe_020 09.04.	Probe_021 09.04.	Probe_022 09.04.
	Probenart		Material	Material	Sedimentationsstaub						
1.	Natrium	Na2O	19,64	19,10	3,13	14,30	11,25	14,44	7,95	14,11	
2.	Kalium	K2O	0,48	0,50	1,67	0,56	1,34	1,78	1,90	0,55	
3.	Bor	B2O3		11,10							
4.	Magnesium	MgO	4,38	3,65	7,78	2,44	1,54	2,21	1,71	2,02	
5.	Calcium	CaO	8,50	8,29	15,76	7,91	11,37	9,16	12,65	8,24	
6.	Barium	BaO	0,08	0,06							
7.	Aluminium	Al2O3	2,34	1,60	22,92	3,94	2,56	2,67	3,47	2,57	
8.	Silicium	SiO2	64,09	54,50	41,56	70,85	71,94	69,74	72,32	72,51	
	KI-Index		28,40	39,50	-17,50	17,33	20,38	22,25	17,27	19,78	2